



Meets the requirements of ASTM D 4434, Type III

Features and Components

Non-wicking Reinforced Polyester Scrim: Our fully integrated manufacturing process adds tensile strength and toughness. Edge sealant is not a requirement for cut edges.

Excellent Chemical Resistance: JM PVC is inherently resistant to oils, air conditioning coolants, fuels and grease.

Energy Savings: The white membranes provide exceptional reflectivity and emissivity for energy savings.



Color

White

JM Membranes are designed with a cap, core, and bottom in order to utilize recycled content. The cap, or top-side is produced with non-recycled content, and should always be install facing up. The cap is identified by the lap line and production code.

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS			
	HA	CA	CA	HW	HA	CA	HW	SA
Do not use with Multi-Ply systems								

Single Ply	TPO		PVC		EPDM		
	MF	FA	MF	FA	MF	FA	BA
Compatible with the selected Single Ply systems above							

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened FA = Fully Adhered BA = Ballasted

Energy and the Environment

Standard		Reflectivity	Emissivity
CRRC®	White	Initial	0.86
		3 Yr. Aged	0.70
CA Title 24	White	Pass	0.86
ENERGY STAR®	White	Initial	0.86
		3 Yr. Aged	0.70
LEED® (SRI)	White	Initial	108
		3 Yr. Aged	84
Recycled Content	Post-consumer	0%	
	Post-industrial	0% - 10%	

The LEED® Solar Reflectance Index (SRI) is calculated per ASTM E1980.

Peak Advantage® Guarantee Information

Product Thickness	Terms
80 mil	5, 10, 15 or 20 yr NDL

Guarantee terms are for mechanically fastened and fully adhered systems. Mixed-membrane jobs – JM PVC SD Plus and JM PVC (KEE) – will not be eligible for a JM Peak Advantage Guarantee.

Codes and Approvals



Installation/Application



Refer to JM PVC application guides and detail drawings for instructions.

Packaging and Dimensions

Sizes	Coverage	
5' x 75' (1.52 m x 22.9 m)	375 ft² (34.84 m²)	
10' x 75' (3.05 m x 22.9 m)	750 ft² (69.67 m²)	
Widths	5'	10'
Rolls per Pallet	9	9
Pallet Weight - lb (kg)	1871 (848.7)	3847 (1745)
Pallets per Truck*	17	8
Producing Locations	Lancaster, SC and Pawtucket, RI	

*Assumes 48' flatbed truck.

JM PVC accessories are formulated to be compatible with JM PVC SD Plus and JM PVC.

Meets the requirements of ASTM D 4434, Type III

Manufactured Physical Properties

Physical Properties		ASTM Test Method	ASTM Requirements	80 mil Result
Strength	Breaking Strength, min, lbf/in (N)	D 751	200 (890)	240 (1,068)
	Elongation at Break, min, %	D 751	15	15
	Tearing Strength, min, lbf (N)	D 751	45 (200)	45 (200)
	Seam Strength, min, % of breaking strength	D 751	75	80
	Static Puncture Resistance lbf (kg)	D 5602	Pass @ 33 (15)	Pass
	Dynamic Puncture Resistance J	D 5635	Pass @ 20	Pass
Longevity	Thickness, min, in.	D 751	+/- 10% from Nominal	0.080 Nominal
	Thickness Over Scrim, min, in.	D 7635	0.016	0.036
	Change in Weight After Immersion in Water, max, %	D 570 modified	3.0	3.0
	Low Temperature Bend, °F	D 2136	No cracks @ -40° F	Pass
Heat Aged Performance	Properties after Heat Aging, min	D 3045	56 days @ 176° F	
	Breaking Strength, %	D 751	90	>90
	Elongation, %	D 751	90	>90
	Linear Dimensional Change, max, % after 6 hrs @ 176° F	D 1204	0.5	<0.5
Weather Performance	Accelerated Weathering, min	G 151 & G 154	5,000 hrs	
	Cracking (@7x magnification)	G 154	No cracks	Pass
	Discoloration (by observation)	G 154	Negligible	Negligible
	Crazing (@7x Magnification)	G 154	No crazing	Pass