

JM EPDM R 75 mil

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Features and Components

Membrane: Cured EPDM (ethylene propylene diene monomer) reinforced with a tough 1,000+ denier polyester mat. Excellent puncture and hail resistance.

Fully Extruded: Produces fewer air voids, more uniform thickness and smoother sheets.

Vulcanization Process: Combines two layers of membrane to produce a fully cross-linked monolithic membrane.

Polymer Formulation: Performs in extreme temperature climates and withstands differential movement (elongation).

UV-Stabilization Properties: Offers outstanding ozone and weather resistance delivering one of the longest service lives available.

Technical Expertise: Backed by 30+ years of EPDM experience and installations.





Color Black

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Ilti-Ply	BUR		APP		SBS				≧ TP0		PO	PVC		EPDM		
	HA	CA	CA	HW	HA	CA	HW	SA	gle	MF	FA	MF	FA	MF	FA	BA
ğ	Do not use with Multi-Ply systems							Sin		Compatible	with the se	lected Sir	ngle Ply sys	tems abo	ove	
Key:	HA =	Hot Applied	d CA =	= Cold Ap	plied H	W = Heat	Weldable	SA =	Self Adhered	MF	= Mechanio	cally Fasten	ed FA =	Fully Adhe	red B A	A = Ballasted

Energy and the Environment

Property	Value
Reflectivity* (ASTM C 1549)	0.06
Emissivity* (ASTM C 1371)	0.88
Post-consumer Recycled Content	0%
Pre-Consumer Recycled Content	0%

*Test methods for reflectivity and emissivity are LEED®- and CRRC®-approved.

Peak Advantage® Guarantee Information

Enhanced guarantees are now available on certain systems for wind and puncture. Consult your local sales representative for more information and for specific guarantee terms and costs

Product	Guarantee Term
When used in most JM EPDM Systems*	Up to 25 years

*Contact JM Technical Services for specific systems.

Codes and Approvals



Installation/Application



Refer to JM EPDM Application Guides and Detail Drawings for instructions.

Packaging and Dimensions

Roll Size	10' x 100' (3.05 m x 30.48 m)				
Roll Coverage	1000 ft ² (92.66 m ²)				
Extruded In:	Milan, OH				

Refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the Web at www.jm.com/roofing.



JM EPDM R 75 mil

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Tested Physical Properties

Physic	al Properties	ASTM Test Method	Standard for ASTM D 4637, Type II	JM EPDM – R 75 mil	
Strength	Breaking Strength (lbf)	D 751 A	> = 90	287	
	Elongation at Fabric Break, Ultimate (%)	D 751 A	> = 15	MD 35, XMD 36*	
	Elongation, Ultimate (%)	D 412	> = 250	482	
	Tear Strength (lbf)	D 751 B	> = 10	104	
	Dynamic Puncture Resistance, 10J, Type II	D 5635	pass	pass	
	Static Puncture Resistance, 55.1 lbf, Type II	D 5602	pass	pass	
	Overall Sheet Thickness (in.)	D 751	+/- 10%	pass	
ity	Thickness Over Scrim, Weathering Side (in.)	D 7635	0.015	0.033	
Longevity	Brittleness Point (°F)	D 2137	< = -49	pass	
	Ozone Resistance	D 1149	pass	pass	
	Water Absorption (mass %)	D 471	< = 8	0.1	
Heat Aged Performance	Heat Aged 670 hrs @ 240°F	D 573			
	Breaking Strength (lbf)	D 751	> = 80	297	
	Elongation, Ultimate (%)	D 412	> = 200	284	
	Linear Dimensional Change (%)	D 1204	< ± 1	0.02	
Weathering	Weathering Resistance, 5040 KJ/(m2-nm) @ 340 nm	D 4637 / G 151 / G 155			
Weat	Visual Inspection	-	pass	pass	

* MD = Machine Direction

XMD = Cross-Machine Direction